


AMENDED SPECIFICATION

PATENT SPECIFICATION



406,345

Application Date (In United Kingdom): Aug. 24, 1932. No. 23742/32.

Accepted: Feb. 26, 1934.

COMPLETE SPECIFICATION

Improvements in or relating to the Production of Formic Acid

40 and zirconium. Thus we may use primary

The apparatus which may be employed 80

[Pr

for conducting the reaction may be of any convenient type and preferably one in which the temperature of exothermic reactions can be readily controlled at the desired temperature. Owing to the corrosive action of formic acid, the interior of the converter and conduits therefrom should preferably be protected. This may be accomplished by using glass or glass-lined apparatus or by coating the inner surfaces of the apparatus with chromium or silver or using for the construction of this equipment acid-resisting alloys of, for example, molybdenum, cobalt, tungsten, chromium, manganese or nickel.

The following examples will illustrate methods of practicing the invention, although the invention is not limited thereto.

EXAMPLE 1.

A gaseous mixture consisting of 90 parts by volume of carbon monoxide, and 20 parts by volume of steam is passed at a pressure of 700 atmospheres and a temperature of 325° C. over an acid zinc phosphate catalyst. This catalyst may be prepared by adding to an aqueous phosphoric acid solution a suitable amount of zinc oxide and subsequently impregnating a support, such as activated charcoal, with this solution. After drying the catalyst at approximately 120° C. it is ready for use. Upon condensation of the reaction product a condensate will be obtained containing formic acid.

EXAMPLE 2.

A gaseous mixture comprising 95 parts by volume of carbon monoxide and 20 parts by volume of steam is passed over a primary calcium phosphate catalyst at a pressure of 200 atmospheres and a temperature of approximately 325° C. A good yield of formic acid admixed with other aliphatic carboxylic acids will be obtained.

EXAMPLE 3.

A gaseous mixture consisting of 90 parts by volume of carbon monoxide, and 20 parts by volume of steam was passed at a pressure of 700 atmospheres and a temperature of 325° C. over a silico-tungstic acid catalyst. This catalyst was prepared by mixing a solution of sodium silicate with a solution of sodium tungstate containing an equivalent amount of sodium tungstate. The resulting solution was acidified with hydrochloric acid and extracted with ether. The ether was evaporated from the extract and the residue taken up with water, the aqueous solution of the residue being used to impregnate silica gel. This catalyst was disposed in a suitable type of reaction chamber for conducting exothermic

gaseous reactions. Upon condensation of the reaction product, a condensate containing a high percentage of formic acid was obtained.

EXAMPLE 4.

A gaseous mixture comprising 95 parts by volume of carbon monoxide and 20 parts by volume of steam was passed over a silico-molybdic acid catalyst. The pressure during the reaction is maintained at approximately 200 atmospheres and the temperature at approximately 325° C. A good yield of formic acid admixed with other aliphatic carboxylic acids will be obtained.

We do not claim the use of catalysts containing substantial quantities of iron, nickel or cobalt, or their compounds.

Having now particularly described and ascertained the nature of our said invention and in what manner the same is to be performed, we declare that, subject to the preceding disclaimer, what we claim is:—

1. A process for the production of formic acid which comprises passing a mixture of carbon monoxide and steam over a non-volatile catalyst comprising an acid salt derived from an acidic oxide of phosphorus, arsenic, tungsten, molybdenum, uranium, chromium vanadium, titanium, boron, silicon, or zirconium.

2. A process as claimed in claim 1, in which the acid salt is a primary or secondary phosphate of zinc, calcium, magnesium, sodium, potassium, copper, cerium, or thorium, or the acid salts formed between these metals and the oxides of tungsten or molybdenum.

3. A process for the production of formic acid which comprises passing a mixture of carbon monoxide and steam over a non-volatile catalyst comprising two or more mutually combined acidic oxides of phosphorus, arsenic, tungsten, molybdenum, uranium, chromium, vanadium, titanium, boron, silicon or zirconium.

4. A process as claimed in claim 3, in which the catalyst comprises phosphomolybdic acid, phospho-tungstic acid, phospho-silicic acid, chromium vanadate, vanadium molybdate, silico-tungstic acid, or silico-molybdic acid.

5. A process as claimed in claim 1, 2, 3 or 4, in which the reaction temperature is 100—400° C., preferably 200—300° C.

6. A process as claimed in claim 1, 2, 3, 4 or 5, in which the reaction is effected under pressure, e.g. 25—900 atmospheres.

7. A process for the production of formic acid, substantially as hereinbefore described.

8. Formic acid, whenever prepared by the process claimed in any of claims 1—7.

Dated the 24th day of August, 1932.

E. C. G. CLARKE,
Imperial Chemical House,
Millbank, London, S.W.1,
Solicitor for the Applicants.

Leamington Spa: Printed for His Majesty's Stationery Office, by the Courier Press.—1935.